

3019 Boucle Houndstooth was tested and met the following flammability requirements:

CA TB 117-2013

ISO/IEC 17025 Third Party Test Report

FILE: DESTEX.A100422C

SAMPLE IDENTIFIED BY CLIENT AS:

Fabric Submitted
Ref #: 3019 501 / Boucle Houndstooth
Lot #: 1033354-9763
Color Blue/Teal Multi

NFPA 260

STANDARD METHODS OF TEST AND CLASSIFICATION SYSTEM FOR
CIGARETTE IGNITION RESISTANCE OF COMPONENTS OF UPHOLSTERED FURNITURE

SECTION 6.1 COVER FABRIC

	<u>CHAR LENGTH (mm)</u>
Sample #1:	13.0
Sample #2:	14.0
Sample #3:	15.0

RESULTS:

Evidence Of Ignition: No.

RESULTS: Class I

6.1.9. If an obvious ignition occurs on any of the three specimens, the smoldering materials shall be extinguished, and the sample shall be recorded as a Class II cover fabric based on the results of this test.

6.1.10. If no obvious ignition occurs, the char on the vertical panel measured from the original crevice position to the highest part of the destroyed or degraded cover fabric shall be recorded to the nearest 2.5 mm.

7.2 Cover Fabric Classification

7.2.1. Class I - Class I cover fabric shall meet the criteria of 7.2.1.1 and 7.2.1.2.

7.2.1.1. When subjected to the cover fabric test, a specimen shall show no evidence of ignition on any test assembly.

7.2.1.2. The vertical char on any of the three specimens shall not exceed 45 mm.

7.2.2. Class II - Cover fabrics that do not meet Class I criteria shall be designated as Class II.

Signed For The Company By


Joseph Lin
Laboratory Manager




Stacy Sawoy
Quality Assurance Manager

CS/10