

3815 Big Texture was tested and met the following flammability requirements:

CA TB 117-2013



Received:02/17/2017	Completed:02/21/2017	Letter: H	BG	P.O.#:	Test Report #:	3-17789-0-
Client's Identification	Style: 3815 Big Texture. Fiber Content: 43% Acrylic, 57% Polyester. Finish: Stain Repellant. Weight: 637 g/m ² . Color: Beige. End Use of Fabric: Upholstery.					
Tested For: Blanca Guerrero	Designtex 200 Varick Street, 8 fl. New York, NY 10014			Key Test: CA TB 117-2013 (Section 1-Cover Fabric) /ACT		235
			Tel: 1-(212)-886-8212		Ext:	
			Fax: 1-(212)-886-8159			

Test Category: Cigarette Ignition Specifier: ACT LE 2015; V 08/15 NTR 9/15
 Product Category: Upholstery PC: 24H dl/SM

TEST PERFORMED: California Technical Bulletin 117-2013 - Requirements, Test Procedure and Apparatus for Testing the Smolder Resistance of Materials Used in Upholstered Furniture (June 2013 Version)

Section 1, Cover Fabric Test (Upholstery cover material is the outermost layer of fabric or related material used to enclose the main support system or upholstery materials, or both, used in the furniture item.) --

As cited by the ACT Voluntary Performance Guidelines (January 2015)

REFERENCE: ASTM E1353-08ae1

IGNITION SOURCE: SRM 1196 Cigarette

SPECIMEN TEST COMPOSITE:

Upholstery Cover Material: As described in "Client's Identification".

Standard Substrate Material: Non FR polyurethane foam, density 1.8 ± 0.05 lb/ft³

BRIEF DESCRIPTION OF TEST: Miniature cushions are prepared using the client's cover fabric over the standard filling material. The vertical or back cushions measure 8" x 8" x 2". The horizontal or seat cushions measure 8" x 5" x 2".

A lighted cigarette is placed in the crevice formed by the vertical cushion and the horizontal cushion.

The test is terminated at 45 minutes if smoldering is no longer observed.

Test measurements and observations are recorded.

-- See Page 3 for "Results" and "Conclusion" --



Received:02/17/2017	Completed:02/21/2017	Letter: H	BG	P.O.#:	Test Report #:	3-17789-0-
Client's Identification	Style: 3815 Big Texture. Fiber Content: 43% Acrylic, 57% Polyester. Finish: Stain Repellant. Weight: 637 g/m ² . Color: Beige. End Use of Fabric: Upholstery.					
Tested For: Blanca Guerrero Designtex 200 Varick Street, 8 fl. New York, NY 10014	Key Test: CA TB 117-2013 (Section 1-Cover Fabric) /ACT Tel: 1-(212)-886-8212 Fax: 1-(212)-886-8159					235 Ext:

PASS/FAIL/REPEAT CRITERIA: A material is considered to pass or fail based on the following criteria:

1. A single mock-up test specimen fails to meet the requirements of this test procedure if any of the following criteria occurs:
 - a) The mock-up test specimen continues to smolder after the 45 minute test duration;
 - b) A vertical char length (measured as specified in step 11.9 of ASTM E1353-08ae1) of more than 1.8 inches (45 mm) develops on the cover fabric.
 - c) The mock-up test specimen transitions to open flaming.
2. The cover fabric passes the test if three initial mock-up specimens pass the test, i.e., the cigarettes burn their entire length and the mock-ups are no longer smoldering.
3. If more than one initial specimen fails, the cover fabric fails the test.
4. If any one of the three initial specimens fails, repeat the test on additional three specimens.
5. If all three additional specimens pass the test, the cover fabric passes the test. If any one of the additional three specimens fails, the cover fabric fails the test.

DISCUSSION: The current version of California Technical Bulletin 117-2013 has no provision to recognize cigarettes that self-extinguish prior to burning their entire length. However, ASTM E 1353 does recognize this phenomenon.

The Govmark report evaluates replacement cigarettes as follows:

If a cigarette self-extinguishes (SE) before burning its entire length, a new cigarette is placed into the test. If the new (replacement) cigarette self-extinguishes or burns its entire length, the result for that specimen will then be evaluated as if the cigarette burned its entire length when assigning the "Passing/Failure" conclusion.



Received:02/17/2017 Completed:02/21/2017 Letter: H BG P.O.#: Test Report #: 3-17789-0-

Client's Identification Style: 3815 Big Texture. Fiber Content: 43% Acrylic, 57% Polyester. Finish: Stain Repellant. Weight: 637 g/m². Color: Beige. End Use of Fabric: Upholstery.

Tested For: **Blanca Guerrero** Key Test: CA TB 117-2013 (Section 1-Cover 235
 Designtex Fabric) /ACT
 200 Varick Street, 8 fl. Tel: 1-(212)-886-8212 Ext:
 New York, NY 10014 Fax: 1-(212)-886-8159

RESULTS:

	Specimen #	Char Length (inches)	SE (yes/no)	SB45 (yes/no)	TOF (yes/no)
Initial:	1	0.3	No	No	No
	2	0.3	No	No	No
	3	0.4	No	No	No
Replacement: (If needed)	1				
	2				
	3				
Repeat Tests: (If needed)	1				
	2				
	3				

EXPLANATION:

Initial: These are the first 3 cigarettes where the results could be sufficient to draw a test conclusion.

Replacement: If any of the initial cigarettes self-extinguish before burning their complete length, a new test is conducted with a fresh cigarette.

Repeat Test: Depending on the initial or replacement results, 3 repeat tests might be required to draw a conclusion.

CODES USED:

SE = Cigarette self-extinguished; See "Discussion" on Page 2
 SB45 = Smolder beyond 45 minutes
 TOF = Transitions to open flaming
 MNR = Measurement not recorded as smoldering exceeded 45 minutes or specimen transitioned to open flames
 EC = Escalating smoldering combustion: Extinguished by technician at:
 (mm: ss) _____ : _____ due to unsafe conditions.

CONCLUSION:

The above results reported for the initial and / or replacement cigarettes are sufficient to indicate:

Passing; Failure; Repeat test on 3 additional specimens

The results after conducting the repeat tests indicate:

Passing; Failure



96-D Allen Boulevard
 Farmingdale, New York 11735-5626 USA
 Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
 e-mail: testing@govmark.com

Received:02/17/2017	Completed:02/21/2017	Letter: H	BG	P.O.#:	Test Report #:	3-17789-0-
Client's Identification	Style: 3815 Big Texture. Fiber Content: 43% Acrylic, 57% Polyester. Finish: Stain Repellant. Weight: 637 g/m ² . Color: Beige. End Use of Fabric: Upholstery.					
Tested For: Blanca Guerrero	Designtex 200 Varick Street, 8 fl. New York, NY 10014			Key Test: CA TB 117-2013 (Section 1-Cover Fabric) /ACT		235
				Tel: 1-(212)-886-8212	Ext:	
				Fax: 1-(212)-886-8159		

REMARKS: None.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

Phyllis Pettit

AUTHORIZED SIGNATURE
 GOVMARK
 /mo

lgb

FEB 24 2017

(Page 4 of 4)



Received:02/17/2017 Completed:02/21/2017 Letter: HI RV P.O.#: Test Report #: 3-17789-1-

Client's Identification Style: 3815 Big Texture. Fiber Content: 43% Acrylic, 57% Polyester. Finish: Stain Repellant. Weight: 637 g/m². Color: Beige. End of Use: Upholstery.

Tested For: **Blanca Guerrero** Key Test: AATCC 8 or 116 Crocking/ACT 95
 Designtex
 200 Varick Street, 8 fl. Tel: 1-(212)-886-8212 Ext:
 New York, NY 10014 Fax: 1-(212)-886-8159

Test Category: Crocking Specifier: ACT NTR 4/16 PC: 4H LE 2015; V 08/15 /dl SM/mg

TEST PERFORMED:

- AATCC Test Method 8 - Colorfastness to Crocking: AATCC Crockmeter Method, as specified for certain products
- AATCC Test Method 116 - Colorfastness to Crocking: Rotary Vertical Crockmeter Method, as specified for drapery prints
 As cited by the ACT Voluntary Performance Guidelines (January 2015)
 Evaluated by comparison with AATCC Chromatic Transference Scale

ACCEPTANCE CRITERIA

PRODUCT CATEGORY:	DRY:	WET:
<input checked="" type="checkbox"/> Upholstery	Grade 4 minimum	Grade 3 minimum
<input type="checkbox"/> Direct Glue Wallcoverings	Grade 3 minimum	Grade 3 minimum
<input type="checkbox"/> Wrapped Panels & Upholstered Walls	Grade 3 minimum	Grade 3 minimum
<input type="checkbox"/> Drapery (solid)	Grade 3 minimum	Grade 3 minimum
<input type="checkbox"/> Drapery (print)	Grade 3 minimum	Grade 3 minimum

RESULTS: Color Transfer to Transfer Cloth

Rating

Dry: Grade 4.5
 Wet: Grade 5

- RATING SYSTEM:
- Grade 5 - No color transfer
 - Grade 4 - Slight color transfer
 - Grade 3 - Moderate color transfer
 - Grade 2 - Considerable color transfer
 - Grade 1 - Excessive color transfer

CONCLUSION: Based on the reported Results and cited Acceptance Criteria, the item tested:

Complies; Does not comply

REMARKS: None.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

FEB 24 2017

AUTHORIZED SIGNATURE

Phyllis Pettit

GOVMARK
 /mo /gb

(Page 1 of 1)



Received: 02/17/2017 Completed: 02/23/2017 Letter: H2 CT P.O.#: Test Report #: 3-17789-2-

Client's Identification Style: 3815 Big Texture. Fiber Content: 43% Acrylic, 57% Polyester. Finish: Stain Repellant. Weight: 637 g/m². Color: Beige. End of Use: Upholstery.

Tested For: **Blanca Guerrero** Key Test: AATCC 16 Lightfast/ACT 40hrs 96
 Designtex
 200 Varick Street, 8 fl. Tel: 1-(212)-886-8212 Ext:
 New York, NY 10014 Fax: 1-(212)-886-8159

Test Category: Light Fastness Specifier: ACT NTR 9/15 LE 2015; V 08/15
 PC: NS d1/SM

TEST PERFORMED: AATCC Test Method 16 - Colorfastness to Light:

- Option 1: Carbon Arc, Continuous Light
- Option 3: Water Cooled Xenon Arc Lamp, Continuous Light

As cited by the ACT Voluntary Performance Guidelines (January 2015)

Evaluated by comparison with AATCC Gray Scale for Evaluating Change in Color

PRODUCT CATEGORY:	ACCEPTANCE CRITERIA:
<input checked="" type="checkbox"/> Upholstery - Woven Fabrics	40 hours - Grade 4 minimum [CODE 96]
<input type="checkbox"/> Direct Glue Wallcoverings	40 hours - Grade 4 minimum [CODE 96]
<input type="checkbox"/> Wrapped Panels & Upholstered Walls	40 hours - Grade 4 minimum [CODE 96]
<input type="checkbox"/> Drapery	60 hours - Grade 4 minimum [CODE 133]

RESULTS:

Number of Hours	Rating
40	Grade 3

REMARKS: None.


RATING SYSTEM:

- Grade 5 - No fading or color change
- Grade 4 - Slight fading or color change
- Grade 3 - Noticeable fading or color change
- Grade 2 - Considerable fading or color change
- Grade 1 - Excessive fading or color change

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

Complies; Does not comply

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.


 AUTHORIZED SIGNATURE

Phyllis Pettit

FEB 24 2017

GOVMARK
 CT/mo lgb



Received:02/17/2017 Completed:02/21/2017 Letter: H3 RV P.O.#: Test Report #: 3-17789-3-

Client's Identification Style: 3815 Big Texture. Fiber Content: 43% Acrylic, 57% Polyester. Finish: Stain Repellant. Weight: 637 g/m². Color: Beige. End of Use: Upholstery.

Tested For: **Blanca Guerrero** Key Test: ASTM D 3511/ACT 140
 Designtex
 200 Varick Street, 8 fl. Tel: 1-(212)-886-8212 Ext:
 New York, NY 10014 Fax: 1-(212)-886-8159

Test Category: Brush Pilling Specifier: ACT LE 2015; V 08/15 PC: 4H dl/SM
 NTR 7/16

TEST PERFORMED: ASTM D 3511 - Standard Test Method for Pilling Resistance and Other Related Surface Changes of Textiles Fabrics: Brush Pilling Tester Method (LE 2013; V 3/15) --

As cited by the ACT Voluntary Performance Guidelines (January 2015)

PRODUCT CATEGORY: Upholstery - Woven Fabrics

ACCEPTANCE CRITERIA: Class 3 Minimum Average

RESULTS:

Specimen #	Rating
1	Class 5
2	Class 5
3	Class 5

Avg:	Class 5

OBSERVATIONS:

Development of fuzzing observed: [] Yes; [x] No
 Color change observed: [] Yes; [x] No
 Loss of cover observed: [] Yes; [x] No

REMARKS: None.

RATING SYSTEM:

- Class 5 - No pilling
- Class 4 - Slight pilling
- Class 3 - Moderate pilling
- Class 2 - Severe pilling
- Class 1 - Very severe pilling



Received:02/17/2017	Completed:02/21/2017	Letter: H3	RV	P.O.#:	Test Report #:	3-17789-3-
Client's Identification	Style: 3815 Big Texture. Fiber Content: 43% Acrylic, 57% Polyester. Finish: Stain Repellant. Weight: 637 g/m ² . Color: Beige. End of Use: Upholstery.					
Tested For: Blanca Guerrero	Key Test: ASTM D 3511/ACT				140	
Designtex 200 Varick Street, 8 fl. New York, NY 10014	Tel: 1-(212)-886-8212		Ext:			
	Fax: 1-(212)-886-8159					

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

Complies; Does not comply

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

Phyllis Pettit

AUTHORIZED SIGNATURE
 GOVMARK

FEB 24 2017

/mo /gb

(Page 2 of 2)



Received:02/17/2017 Completed:02/21/2017 Letter: H4 RV P.O.#: Test Report #: 3-17789-4-

Client's Identification Style: 3815 Big Texture. Fiber Content: 43% Acrylic, 57% Polyester. Finish: Stain Repellant. Weight: 637 g/m². Color: Beige. End of Use: Upholstery.

Tested For: **Blanca Guerrero** Key Test: ASTM D 5034/ACT 140
 Designtex
 200 Varick Street, 8 fl. Tel: 1-(212)-886-8212 Ext:
 New York, NY 10014 Fax: 1-(212)-886-8159

Test Category: Tensile Specifier: ACT LE 2015; V 08/15 PC: 8H d1/SM
 NTR 9/15

TEST PERFORMED: ASTM D 5034 - Standard Test Method for Breaking Force of Textile Fabrics (Grab Test) --

As cited by the ACT Voluntary Performance Guidelines (January 2015)

PRODUCT CATEGORY: ACCEPTANCE CRITERIA (for warp and weft):

 Upholstery 50 lbs. minimum average
 Wrapped Panels & Upholstered Walls 35 lbs. minimum average
 Draperies No requirement

RESULTS:

Direction	Specimen #	(lbs)
Warp:	1	441
	2	410
	3	414
	4	427
	5	433
	Avg:	425
Weft:	1	316
	2	332
	3	339
	4	345
	5	364
	6	332
	7	336
	8	302
Avg:	333	

REMARKS: None.

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

Complies; Does not comply; Does not apply to drapery fabrics



96-D Allen Boulevard
 Farmingdale, New York 11735-5626 USA
 Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
 e-mail: testing@govmark.com

Received:02/17/2017	Completed:02/21/2017	Letter: H4	RV	P.O.#:	Test Report #:	3-17789-4-
Client's Identification	Style: 3815 Big Texture. Fiber Content: 43% Acrylic, 57% Polyester. Finish: Stain Repellant. Weight: 637 g/m ² . Color: Beige. End of Use: Upholstery.					
Tested For: Blanca Guerrero	Key Test: ASTM D 5034/ACT				140	
DesignTex 200 Varick Street, 8 fl. New York, NY 10014	Tel: 1-(212)-886-8212		Ext:			
	Fax: 1-(212)-886-8159					

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

Phyllis Pettit

 AUTHORIZED SIGNATURE

GOVMARK

/mo /gb

FEB 24 2017

(Page 2 of 2)



Received:02/17/2017 Completed:02/21/2017 Letter: H5 RV P.O.#: Test Report #: 3-17789-5-

Client's Identification Style: 3815 Big Texture. Fiber Content: 43% Acrylic, 57% Polyester. Finish: Stain Repellant. Weight: 637 g/m². Color: Beige. End of Use: Upholstery.

Tested For: **Blanca Guerrero** Key Test: ASTM D 4034/ACT 150
 Designtex
 200 Varick Street, 8 fl. Tel: 1-(212)-886-8212 Ext:
 New York, NY 10014 Fax: 1-(212)-886-8159

Test Category: Seam Slippage Specifier: ACT LE 2015; V 08/15 PC: 8H d1/SM
 NTR 6/16

TEST PERFORMED: ASTM D 4034 - Standard Test Method for Resistance to Yarn Slippage at the Sewn Seam in Woven Upholstery Fabrics - Plain, Tufted, or Flocked --

As cited by the ACT Voluntary Performance Guidelines (January 2015)

PRODUCT CATEGORY: Upholstery

ACCEPTANCE CRITERIA: 25 lbf minimum average for warp and weft

SEAM CONSTRUCTION:

Seam Allowance: 0.5"
 Seam Type: 301 Lockstitch
 Thread Type: 100% Nylon Bonded Monocord;
 Needle Thread size 8/Bobbin Thread Size 5
 Needle: Size 22 Ball Point
 Stitches/Inch: 7 ± 0.5

RESULTS: Specimen results reported to the nearest 0.5 lb force (lbf)
 Average reported to the nearest 0.5 lb force (lbf)

	Specimen #	(lbf)
Warp Yarn Slippage: (seamed in warp direction)	1	92.5 SS
	2	76.0 SS
	3	76.0 SS
	4	71.0 SS
	5	94.0 SS
	Avg:	82.0
Weft Yarn Slippage: (seamed in weft direction)	6	138.5 SB
	7	103.5 SB
	8	160.0 SB
	9	115.0 SB
	10	144.5 SB
	Avg:	132.5

ABBREVIATIONS WHICH MAY BE USED:

- SS = Seam Slippage
- SB = Seam break before 1/4" slippage
- FB = Fabric break before 1/4" slippage
- FBS = Fabric break at Seam before 1/4" slippage


Received:02/17/2017	Completed:02/21/2017	Letter: H5	RV	P.O.#:	Test Report #:	3-17789-5-
Client's Identification	Style: 3815 Big Texture. Fiber Content: 43% Acrylic, 57% Polyester. Finish: Stain Repellant. Weight: 637 g/m ² . Color: Beige. End of Use: Upholstery.					
Tested For: Blanca Guerrero	Designtex 200 Varick Street, 8 fl. New York, NY 10014			Key Test: ASTM D 4034/ACT		150
				Tel: 1-(212)-886-8212	Ext:	
				Fax: 1-(212)-886-8159		

REMARKS: None.

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

Complies; Does not comply

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.



Phyllis Pettit

 AUTHORIZED SIGNATURE

GOVMARK

/mo

lgb

FEB 24 2017

(Page 2 of 2)

Received:02/17/2017	Completed:02/21/2017	Letter: H6	RV	P.O.#:	Test Report #:	3-17789-6-
---------------------	----------------------	------------	----	--------	----------------	------------

Client's Identification	Style: 3815 Big Texture. Fiber Content: 43% Acrylic, 57% Polyester. Finish: Stain Repellant. Weight: 637 g/m ² . Color: Beige. End of Use: Upholstery.
--------------------------------	---

Tested For: Blanca Guerrero Designtex 200 Varick Street, 8 fl. New York, NY 10014	Key Test: ASTM D 4157/ACT 100K Tel: 1-(212)-886-8212 Fax: 1-(212)-886-8159	484 Ext:
---	---	-------------------------------

Test Category:Wyz Abrasion Specifier:ACT LE 2015; VE 08/15 CODE: 100,000 RQ
 PC: 8H NTR 5/16 dl/SM

TEST PERFORMED: ASTM D 4157 Standard Test Method for Abrasion Resistance of Textile Fabrics (Oscillatory Cylinder Method - Wyzenbeek) --

As cited and modified by the ACT Voluntary Performance Guidelines (January 2015)

BRIEF DESCRIPTION OF TEST: The abrading material (abradant) is placed on the rotating (oscillating) cylinder of the tester. The submitted material which is to be evaluated is held in position by four testing arms. Typically, two of the arms support length specimens, and two of the arms support width specimens. The abradant rubs against the submitted material. A back and forth movement is considered a double rub. At specified intervals, the support arms are raised, and the submitted material is visually examined. The result of this visual examination is recorded. The total number of double rubs is dependent upon the client's request. The test is concluded at the number of double rubs requested by the client or when the rating falls below a value of 3.

PRODUCT CATEGORY: Upholstery - Woven Fabric

TEST PARTICULARS (check one from each of items 1 - 3, as applicable):

- 1. Abradant: #10 cotton duck - Specified for all materials except 100% olefin
 Wire (steel) screen -Specified for 100% olefin
- 2. Material with elasticity: Backed with tape to prevent elongation
- 3. Surface Category: Regular surface
 Special surface effect (napped, chenille, embossed, textured, etc.)

TEST CONDITIONS: Specimen Tension: 4 lbs.; Head Pressure (Compression Force): 3 lbs.

RATING SYSTEM FOR REGULAR SURFACE:

- 5 - None or negligible wear
- 4 - Slight wear
- 3 - Moderate wear
- 2 - Noticeable wear (broken yarns, floating yarns, etc.)
- 1 - Severe wear (complete fabric break)

RATING SYSTEM FOR SPECIAL SURFACE EFFECT:

- 5 - None or negligible wear/change of special surface effect
- 4 - Slight wear/change of special surface effect
- 3 - Moderate wear/change of special surface effect
- 2 - Noticeable wear/change of special surface effect (base yarns exposed)
- 1 - Severe wear/change of special surface effect (base yarns exposed and broken)



Received:02/17/2017	Completed:02/21/2017	Letter: H6	RV	P.O.#:	Test Report #:	3-17789-6-
Client's Identification	Style: 3815 Big Texture. Fiber Content: 43% Acrylic, 57% Polyester. Finish: Stain Repellant. Weight: 637 g/m ² . Color: Beige. End of Use: Upholstery.					
Tested For: Blanca Guerrero	Designtex 200 Varick Street, 8 fl. New York, NY 10014			Key Test: ASTM D 4157/ACT 100K		484
				Tel: 1-(212)-886-8212	Ext:	
				Fax: 1-(212)-886-8159		

RESULTS: Visual Observations (see page 1 for Rating System)

# of Double Rubs	Length Specimens	Width Specimens
3,000	4.5	4.5
9,000	4	4
15,000	4	4
22,500	3.5	3.5
30,000	3.5	3.5
40,000	3	3
45,000	3	3
50,000	3	3
55,000	3	3
60,000	3	3
65,000	3	3
70,000	3	3
75,000	3	3
80,000	3	3
85,000	3	3
90,000	3	3
95,000	3	3
100,000	3	2.5
	Moderate loss of surface pile	Broken & floating yarns

NOTE: For tests exceeding 100,000 double rubs, the cotton duck abradant is changed every 100,000 double rubs.

REMARKS: None.

ACCEPTANCE CRITERIA:

Low Traffic/Private Spaces: No yarn breaks or noticeable wear after 15,000 double rubs
 High Traffic/Public Spaces: No yarn breaks or noticeable wear after 30,000 double rubs

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested is rated for:

Low Traffic/Private Spaces; High Traffic/Public Spaces; Unrated

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

Phyllis Pettit

FEB 24 2017

AUTHORIZED SIGNATURE

GOVMARK

MA-8/mo 19b