

6680 Aquatint was tested and met the following flammability requirements:

ASTM E 84 Adhered Class A



Received:05/10/2016 Completed:06/03/2016 Letter: C CT P.O.#: Test Report #: 3-13305-0-

Client's Identification Style: Aquatint 6680. [Also representing Burnish 6678]. 100% Vinyl, Non Woven Back. 15 oz/lin yd.

Tested For: **Teesha Prezeau** Key Test: ASTM E 84/ASTM F793 1195
 Designtex
 357 County Avenue Tel: 1-(201)-917-7738 Ext:
 Secaucus, NJ 07094 Fax: 1-(201)-917-7764

Category: Tunnel Test (Flame Spread & Smoke Developed) Specifier: ASTM F793 PC: ME SM/mg
 LE: 2010a V 03/15

TEST PERFORMED: ASTM F 793 - Standard Classification of Wallcovering by Durability Characteristics, Paragraph 5.2 which references:

ASTM E 84 - Standard Test Method for Surface Burning Characteristics of Building Materials

APPROXIMATE THICKNESS OF SPECIMEN (as measured by Govmark): 0.020"

PRODUCT CATEGORY:

- Textile Type Product
- Vinyl Type Product
- Other than Textile Type or Vinyl Type Product: _____

* Note: Textile or expanded vinyl wallcoverings classified by this procedure are limited to use in sprinklered areas in certain public occupancies. If textile or expanded vinyl wallcoverings are used in non-sprinklered areas, the NFPA 265 corner fire test is mandated.

For other interior finish products in non-sprinklered areas, a room corner fire test also applies. This would be NFPA 286.

CLASSIFICATION APPLIED FOR:	CLASSIFICATION CRITERIA:
<input type="checkbox"/> Category IV, Type I	Maximum Flame Spread: 25 Maximum Smoke Developed: 450
<input checked="" type="checkbox"/> Category V, Type II	Maximum Flame Spread: 25 Maximum Smoke Developed: 450
<input type="checkbox"/> Category VI, Type III	Maximum Flame Spread: 25 Maximum Smoke Developed: 450

REMARKS: None.



Received:05/10/2016	Completed:06/03/2016	Letter: C	CT	P.O.#:	Test Report #:	3-13305-0-
Client's Identification	Style: Aquatint 6680. [Also representing Burnish 6678]. 100% Vinyl, Non Woven Back. 15 oz/lin yd.					
Tested For: Teesha Prezeau	Key Test: ASTM E 84/ASTM F793				1195	
DesignTex 357 County Avenue Secaucus, NJ 07094	Tel: 1-(201)-917-7738		Ext:			
	Fax: 1-(201)-917-7764					

SPECIMEN MOUNTING:

- Self Supporting: The test specimen, the face of which was 23" ± 1" x 24', was such that it remained in position in the tunnel during the fire test, and no additional support was required.
- Adhered to IRC: The test specimen was bonded to three 1/4" IRC (Inorganic Reinforced Cement) boards (a cement asbestos substitute) to form a test specimen the face of which was 23" ± 1" x 24'.
- Adhered to Gypsum: The test specimen was adhered to 5/8" thick Type X gypsum board, to form a test specimen the face of which was 23" ± 1" x 24'.
- Unadhered: The 23" ± 1" x 24' specimen was not adhered to any substrate. Instead, it was laid over a 2" hexagonal wire mesh screen and 1/4" rods.
- Other: _____

RESULTS:

Flame Spread Index: 25
 Smoke Developed: 55


DATA SUMMARY:

Time to Ignition: 00.15 minutes
 Maximum Flame Spread "Distance": 05.76 feet
 Maximum Flame Spread "Time": 02.57 minutes

CONCLUSION: Based on the above Results and "Classification Applied For", the item tested:

Complies; Does not comply
 with the Classification Criteria of this specific paragraph of ASTM F 793.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.


 AUTHORIZED SIGNATURE
 GOVMARK
 CT /pm itm
 Ms. Phyllis Pettit
 JUN 06 2016